

**Suzhou Standard Polymer CO., LTD.**

Building 88, No. 116 Wutaishan Road, Suzhou new district , Jiangsu, China

Tel : 86-512-63659176

STD2410019 is a non-halogen fire retardant masterbatch. It can be used in cast film, coating film, and blown film.

STD Code: STD2410019**TECHNICAL DATA SHEET****Test****Target****Method****Apperance:**

Light yellow

STDW02-034

Delta pressure,PSI: ≤ 100

STDW02-007

Moisture,%: ≤ 0.3

STDW02-006

MFI,g/10min:

60-80

STDW02-005

Density,g/cm³:

0.92±0.1

STDW02-020

Hundred-grain weight,g:

1.4±0.3

STDW02-019

The information contained herein is believed to be reliable, but no representations, guarantees or warranties of any kind are made as to its accuracy, suitability for particular applications or the results to be obtained there from. The information is based on laboratory work with small-scale equipment and does not necessarily indicate end product performance. Because of the variation in methods, conditions and equipment used commercially in processing these materials, no warranties or guarantees are made as to the suitability of the products for the application disclosed. Full-scale testing and end product performance are the responsibility of the user. Suzhou Standard Polymer shall not be liable for and the customer assumes all risk and liability of any use or handling of any material beyond Suzhou Standard Polymer Co., Ltd. direct control. Suzhou Standard Polymer makes no warranties, expressed or implied, but not limited to, the implied warranties of merchantability and fitness for a particular purpose.